

MW-G

STD. type heavy foil series

- 适用于较高电流设计板材之符合新一代环保要求之电解铜箔。
MW-G heavy copper foil comply with environment regulation is suitable for use in high current board design.
- 较低的粗糙度特性具优越的蚀刻性。
Good bonding strength./ Excellent heat resistance./ Good etchability.
- 铜箔稳定的量产能力, 可充分供应客户需求。
Our plant has stable capacity for MW-G to fulfill customer requirements.

用途/Application

- 汽车板
/Automotive board
- 与电源供应器
/Power supply unit
- 太阳能板
/ Solar panel

结构 /Composition



生产地点 /Production Site


- 台湾 / Taiwan
- 马来西亚 / Malaysia

特性代表值/Representative data

	μm	Rz (μm)	Tensile Strength (N/mm ²)	Elongation (%)	Peel Strength (kg/cm)
MW-G	105	13.0	300	15	>3.0
	140	14.0	300	15	>3.0
	175	15.0	300	15	>3.0
	210	15.0	300	15	>3.0

※上述表列为代表性数据非保证值。
This is representative data, not guarantee.

处理面 /Laminate side



阻剂面/ Resist side

