

<Tantalum Oxide Ta2O5>

Grade	Properties	Purity (%)	SSA (m ² /g)	Package(example)		Main applications
				Packing	Weight	
High purity grade	White powder	>99.99	2.0~3.0	Exterior Package: Pail can Interior Package: polyethylene double bag	Net20kg	For single crystal
Optical grade		>99.9	1.0~2.5	Exterior Package: Cardboard Interior Package: polyethylene double bag	Net25kg	For optical lens
Ceramic grade			2.5~4.0			Dielectric, piezoelectric, etc. For electronic ceramics

<Niobium Oxide Nb2O5>

Grade	Properties	Purity (%)	SSA (m ² /g)	Package(example)		Main applications
				Packing	Weight	
Optical grade	White powder	>99.9	3.0~4.0	Exterior Package: Pail can Interior Package: polyethylene double bag	Net15kg	For optical lens
Ceramic grade			4.5~6.5			Dielectric, piezoelectric, etc. For electronic ceramics

<Niobium Hydroxide Nb(OH)5>

Grade	Properties	Purity (%)	SSA (m ² /g)	Package(example)		Main applications
				Packing	Weight	
Niobium hydroxide	White powder	-	150~250	Exterior Package: Pail can Interior Package: polyethylene double bag	Net15kg	For catalyst