

Grade	Composition	Particle size (nm)	SSA (m <sup>2</sup> /g)	D50 (μm)	Resistivity (Ωcm)	Coating film (transparency)	
						Transmittance (%)	Haze (%)
<b>6010</b>	SnO <sub>2</sub>	10~20	55	1.0	1.0E+01	80	10
<b>6060</b> ※	SnO <sub>2</sub>	10~20	60	1.4	1.0E+06	80	10
<b>ATO</b> ※	Sb-SnO <sub>2</sub>	10~20	40	1.5	2.0E+00	80	10
<b>PTO</b> ※	P-SnO <sub>2</sub>	10~20	45	4.0	5.0E+00	80	10

※Trial