

Grade	SSA (m <sup>2</sup> /g)	Particle size distribution(μm)			Tapping density (g/cm <sup>3</sup> )	C (wt%)	O (wt%)
		D10	D50	D90			
1110	0.63	1.1	3.6	8.9	3.9	0.11	0.25
1030Y	2.6	0.28	0.42	0.66	3.3	0.20	0.60
1050Y	1.1	0.57	0.81	1.1	4.0	0.15	0.35
1100Y	0.76	0.83	1.1	1.6	4.1	0.15	0.23
1200Y	0.39	1.2	2.1	3.1	4.8	0.12	0.20
1300Y	0.23	2.7	3.5	5.0	5.0	0.13	0.19

※Figures in the table are example data and not specify any certain characters.

※Various surface treatments with both inorganic and organic are available.