

Grade	SSA (m ² /g)	Particle size distribution(μm)			Tapping density (g/cm ³)
		D10	D50	D90	
MA-C02K	0.60	0.9	1.8	3.6	4.2
MA-C025K	0.46	1.0	2.4	5.2	4.6
MA-C03K	0.32	1.3	3.4	6.3	5.0
MA-C05K	0.28	1.7	5.8	12.1	5.3
MA-C05K-2	0.21	2.8	5.1	8.7	5.0
MA-C08K-2	0.15	6.0	8.2	11.1	5.0
MA-CKU	0.16	6.6	11.1	20.7	5.3
MA-C04J	0.44	1.7	4.3	7.2	3.7
MA-C08J	0.24	5.2	8.2	12.3	3.7
MA-CJU	0.15	9.0	17.7	36.1	3.6

※Figures in the table are example data and not specify any certain characters.

※Various surface treatments with both inorganic and organic are available.