

Grade	SSA (m ² /g)	Particle size distribution(μm)			Tapping density (g/cm ³)	Ag (wt%)
		D10	D50	D90		
Spherical powder (10%Ag/1100Y)	0.9	0.8	1.1	1.3	3.5	10
Flake powder (10%Ag/1100YP)	1.4	1.1	2.0	3.3	3.3	10

※Figures in the tables are example data and silver coat is possible for various copper powders.