

Grade	SSA (m ² /g)	Particle size distribution(μm)				Tapping density (g/cm ³)	Shape	Features
		D10	D50	D90	D100			
SPQ03R	1.40	0.5	0.8	1.3	3.9	4.6	Spherical	high dispersity, high sphericity, surface smoothness
SPN05S	0.65	0.8	1.4	2.3	6.5	4.6	Spherical	high dispersity, high sphericity
SPN10JS	0.40	1.2	2.0	3.3	9.3	5.3	Spherical	
SPN20J	0.35	1.6	2.5	4.0	11.0	5.3	Spherical	
SL02	0.29	1.2	2.1	3.5	9.3	5.9	Spherical	high filling, low-temperature sintering
SPH02J	1.66	0.8	1.8	3.6	11.0	2.8	agglomerated powder	particles of aggregates

※Figures in the table are example data and not specify any certain characters.

※Various surface treatments with both inorganic and organic are available.

※Adjustable degree of flatness