

Grade	Composition		Particle size (nm)	SSA (m ² /g)	D50 (μm)	Resistivity (Ωcm)	Coating film (transparency)	
	Coating material	Core material					Transmittance (%)	Haze (%)
4310	SnO ₂	BaSO ₄	100	40	0.5	1.0E+01	90	10
4810	SnO ₂	BaSO ₄	200	30	0.5	2.0E+02	90	20
4410	Sb-SnO ₂	BaSO ₄	100	30	0.5	5.0E+00	90	10
4700	Sb-SnO ₂	BaSO ₄	100	30	0.5	1.0E+01	90	10
4910	SnO ₂	TiO ₂	200	25	1.0	1.0E+02	40	90
8050※	Sb-SnO ₂	SiO ₂	50	70	0.4	1.0E+01	95	5
8080※	Sb-SnO ₂	SiO ₂	80	50	0.5	1.0E+01	95	5

※Trial